



ELECTRONIC SOLDERS

TECHNICAL DATA SHEET 60% TIN/40% LEAD ROSIN CORE

APPLICATIONS

Rosin Core is suitable for use in any commercial hand soldering application- electrical and non-electrical.

TECHNICAL DATA

Color	Gray/Silver
Melting Range	361° - 376° F (solid to liquid)
Tensile Strength	6000 psi
Specific Gravity	8.51%
Density	.3068

ROSIN CHARACTERISTICS

Color	White to yellowish solid
Halogen Content	0 - 2%
Spread Factor	Over 90
Copper Mirror Test	Pass
Corrosion Test	Pass
Storage	Keep in cool dry place

AVAILABILITY

Rosin Core may be obtained in standard tin/lead or other alloys, in diameters from .009 to .125 in flux percentages from 0.5% to 3.6% on 1 pound, 5 pound and 20 pound spools.

1 Crossman Road South, Sayreville, N. J. 08872
Tel: 732-316-2100 ■ Fax: 732-316-2177 ■ Toll Free 800-526-4577
www.solders.com

